

DESCRIPTION

DURAMIX Mortar Additive is a premium grade of Cement Additive imported from Europe. It improves the workability and adhesion of plastering render and brick laying mortar, eliminate shrinkage cracks & speed up masonry works. It is economical to use as it helps to save time & labour, hence increase productivity and at the same time ensuring high quality plaster and mortar mixes.

AREAS OF APPLICATION

1. Masonary laying bricks & block works.
2. Wall plastering render.
3. Floor screed
4. General purpose repair mortar.
5. Suitable for both interior and exterior applications.

TYPICAL MIXING RATIO

Duramix Mortar Additive (100gm) Cement (50kg)
Fine Sand 200kg (40 scoopes) Water (30 liters)

** Recommended mixing time should be more than 5 minutes to ensure optimum homogeneous mix.*


BENEFITS / ADVANTAGES

- * Improve workability of cement sand mortar
- * Improve bonding strength and hardness
- * To replace lime putty or slaked lime for on site mixing
- * Reduce shrinkage crack
- * Smoother & better finishing
- * Economical, save time & labour
- * To ease pumpability in spray machine

All information contained in this brochure is only act as a general guidance as it is not possible to give specific instructions for various site conditions or to control the applications.



Plastering without **DURAMIX** MORTAR ADDITIVE



Plastering with **DURAMIX** MORTAR ADDITIVE

SPECIFICATIONS

- * Colour - Grey
- * Cement - OPC
- * Additives - High polymerisation plasticiser
- * Lime free, as recommended by CIDB

APPLICATION - Mix thoroughly

Cement
1 bag of 50kg OPC

Water
30 litre of water
(6 plaster pails)

Fine Plaster Sand
200kg of fine sand
(40 scoops)

1 packet of Duramix cement mortar additive

SAFETY PRECAUTIONS

1. If contacted with skin, wash with plenty of water
2. If contacted with eyes, seek medical treatment immediately

DURACEMTM
COATING INDUSTRIES SDN BHD

LOT 2772 H, AL 220 Kampung Baru Sungai Buloh
47000 Sungai Buloh, Selangor Darul Ehsan Malaysia.

HL: +603-6140 2129 / +603-6156 7684

FX: +603-6140 3129

Email: sales@DuracemGroup.com

Website: www.DuracemGroup.com